

Issue Date: 05-23-2017
Renewal Date: 01-01-2018

DIVISION: 06 00 00 – WOOD, PLASTICS, AND COMPOSITES
Section: 06 05 73.13 – Fire-Retardant Wood Treatment

REPORT HOLDER:

Fire Retardant Chemical Technologies LLC
3465 Gribble Road
Matthews, NC 28104
980-253-8880

ADDITIONAL LISTEE:

Chicago Flameproof and Wood Specialties Corp.
1200 South Lake Street
Montgomery, IL 60538
630-859-0009

REPORT SUBJECT:

FlameTech™ Fire-Retardant-Treated Wood

1.0 SCOPE OF EVALUATION

1.1 This Research Report addresses compliance with the following Codes:

- 2015, 2012, and 2009 *International Building Code*® (IBC)
- 2015, 2012, and 2009 *International Residential Code*® (IRC)

NOTE: This report references 2015 Code sections with [2012] and [2009] Code sections shown in brackets where they differ.

1.2 FlameTech fire-retardant-treated wood has been evaluated for the following properties (see Table 1):

- Surface burning characteristics
- Strength reduction
- Hygroscopicity
- Corrosion
- Fire resistance

1.3 FlameTech has been evaluated for the following uses (see Table 1):

- Where the Code permits wood or fire-retardant treated wood
- Interior applications

2.0 STATEMENT OF COMPLIANCE

FlameTech fire-retardant-treated wood complies with the Codes listed in Section 1.1, for the properties stated in Section 1.2, and uses stated in Section 1.3, when installed as described in this report, including the Conditions of Use stated in Section 6.

3.0 DESCRIPTION

3.1 FlameTech: Fire-retardant-treated lumber and plywood pressure treated with FlameTech water based interior fire retardant. FlameTech products are kiln dried after treatment to a moisture content of 19 percent for lumber and 15 percent for plywood. Solid dimensional lumber ranging from 2 × 4 to 2 × 16 inches in SPF, Southern Pine, Douglas Fir, and Other Wood species as #2 and higher grades. Structural plywood ranging from 15/32 to 1-1/8 inches C-D Exposure 1 and higher grades.

4.0 PERFORMANCE CHARACTERISTICS

4.1 Surface Burning Characteristics: FlameTech treated lumber and plywood has a flame spread index of 25 or less and smoke developed index of 450 or less when tested in accordance with ASTM E84; exhibits no evidence of significant progressive combustion when continued for an additional 20-minute period and the flame front progression is less than 10-1/2 feet. Refer to Section 2303.2 of the IBC and Section R802.1.5 [R802.1.3] of the IRC. FlameTech treated lumber and plywood complies with ASTM E2768.

4.2 Strength Reduction: Span ratings and total allowable loads for treated plywood in roof sheathing and subfloor applications are provided in Table 2. Roof sheathing is recognized for temperatures up to 170°F (77°C).

Adjustment factors for treated lumber when used at or near room temperatures and for service temperatures to 150°F are provided in Tables 3 and 4, respectively.



The performance of FlameTech fire-retardant-treated plywood has been evaluated to ASTM D5516 and lumber has been evaluated to ASTM D5664. Plywood maximum span ratings and allowable loads have been developed in accordance with ASTM D6305. Lumber treatment adjustment factors have been developed in accordance with ASTM D6841. The base design values for untreated lumber are published in ANSI/AWC NDS-2015 *National Design Specification (NDS) for Wood Construction 2015 Edition*.

4.3 Hygroscopicity: Moisture content of FlameTech treated wood is less than 28 percent when tested at 92 percent relative humidity in accordance with ASTM D3201 and is therefore suitable for interior conditions. Refer to Section 2303.2.7 of the IBC and Section R802.1.5.9 [R802.1.3.7] of the IRC.

4.4 Corrosion: The corrosion rate of hot-dipped galvanized fasteners in contact with FlameTech treated wood used in interior applications is evaluated in accordance with AWWA E12 and ICC-ES AC326.

4.5 Fire Resistance: FlameTech treated lumber and plywood have been tested in accordance with ASTM E119 as components of fire-resistance-rated wall assemblies for 1 hour and 2 hour ratings. See Intertek Design Listings FRCT/FRWT 60-01 and FRCT/FRWT 120-01 in the Intertek Listing Report "[FRCT – FlameTech](#)" on the Intertek Directory of Building Products.

4.5.1 One-Hour Exterior Wall Assembly: When used in Type III, Type IV, and Type V construction, 1 hour fire-resistance-rated assemblies incorporating FlameTech treated wood studs and plywood must be as described in [Intertek Design Listing FRCT/FRWT 60-01](#). The design values for the studs must be adjusted in accordance with Table 3 for service temperatures to 100°F (38°C). The allowable spans for the plywood must be in accordance with the spans listed in Table 2 for FlameTech wall/subfloor.

4.5.2 Two-Hour Exterior Wall Assembly: When used in Type III, Type IV, and Type V construction, 2 hour fire-resistance-rated assemblies incorporating FlameTech treated wood studs and plywood must be as described in [Intertek Design Listing FRCT/FRWT 120-01](#). The design values for the studs must be adjusted in accordance with

Table 3 for service temperatures to 100°F (38°C). The allowable spans for the plywood must be in accordance with the spans listed in Table 2 for FlameTech wall/subfloor.

5.0 INSTALLATION

5.1 General:

FlameTech treated lumber and plywood must be installed in accordance with the manufacturer's published installation instructions, the applicable Code, and this Research Report. A copy of the manufacturer's instructions must be available on the jobsite during installation.

5.2 Application:

Exposure to precipitation during storage or installation shall be avoided. If material does become wet, it shall be replaced or permitted to dry (maximum 19 percent moisture content for lumber and 15 percent moisture content for plywood) prior to covering or enclosure by wallboard or other construction materials (except for protection during construction).

Fasteners, including nuts and washers, shall be hot-dipped galvanized in accordance with FlameTech's published installation instructions.

6.0 CONDITIONS OF USE

6.1 Installation must comply with this Research Report, the manufacturer's published installation instructions, and the applicable Code. In the event of a conflict, this report governs.

6.2 All strength calculations shall be subject to the design value adjustment factors or span ratings shown Tables 2 through 4, and only be used for unincised dimensional lumber and plywood of the species noted in this report.

6.3 FlameTech treated lumber shall not be ripped or milled as this will alter the surface-burning characteristics and invalidate the flame spread classification. Framing end cuts and holes are permitted.

6.4 FlameTech treated lumber and plywood shall not be used in contact with the ground.





6.5 The values in Tables 2 through 4 of this report are applicable under elevated temperatures resulting from cyclic climatic conditions. They are not applicable under continuous elevated temperatures resulting from manufacturing or other processes which shall require special consideration in design, which is not within the scope of this report.

6.6 FlameTech treated lumber and plywood is manufactured at the facility of the listee noted in this report under a quality control program with inspections by Intertek Testing Services NA, Inc. (AA-647).

7.0 SUPPORTING EVIDENCE

7.1 Data in accordance with the ICC-ES Acceptance Criteria Fire Retardant Treated Wood (AC66), Approved June 2015.

7.2 Reports of testing and analysis in accordance with ASTM D5516, D6305, D5664, D3201, E84, E2768, and AWPA E12.

7.3 Intertek Listing Report "FRCT – FlameTech", on the [Intertek Directory of Building Products](#).

8.0 IDENTIFICATION

FlameTech treated lumber and plywood must bear the structural grade mark of an approved agency. In addition, labeling is provided on each plywood panel and lumber piece with the following information:

1. The product name (FlameTech);
2. Name and address of the treater (Additional Listee);
3. Species of wood treated;

4. Flame spread and smoke-developed indices;
5. The Code Compliance Research Report Number (CCRR-1088). Refer to the CCRR for method of drying after treatment and statement of conformance with the applicable Code-referenced standards;
6. The Intertek Mark as shown below.



9.0 OTHER CODES

This section is not applicable.

10.0 CODE COMPLIANCE RESEARCH REPORT USE

10.1 Approval of building products and/or materials can only be granted by a building official having legal authority in the specific jurisdiction where approval is sought.

10.2 Code Compliance Research Reports shall not be used in any manner that implies an endorsement of the product by Intertek.

10.3 Reference to the <https://bpdirectory.intertek.com> is recommended to ascertain the current version and status of this report.

This Code Compliance Research Report ("Report") is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this Report. Only the Client is authorized to permit copying or distribution of this Report and then only in its entirety, and the Client shall not use the Report in a misleading manner. Client further agrees and understands that reliance upon the Report is limited to the representations made therein. The Report is not an endorsement or recommendation for use of the subject and/or product described herein. This Report is not the Intertek Listing Report covering the subject product and utilized for Intertek Certification and this Report does not represent authorization for the use of any Intertek certification marks. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek.





TABLE 1 – Properties Evaluated

Property	2015 IBC Section ⁽¹⁾	2015 IRC Section ⁽¹⁾
Surface burning characteristics	2303.2	R802.1.5
Strength adjustments for plywood	2303.2.5.1	R802.1.5.6
Strength adjustments for lumber	2303.2.5.2	R802.1.5.7
Hygroscopicity	2303.2.7	R802.1.5.9
Corrosion	2304.10.5.4	R317.3.4
Fire resistance	703.2	R302

(1) Section numbers may be different for earlier versions of the International codes.

TABLE 2 – FlameTech Treated Plywood Maximum Spans and Allowable Loads

Performance Category	Untreated Span Rating	Treated Plywood				
		Roof Sheathing				Subfloor
		Maximum Span ⁽⁴⁾ (in.)	Total Allowable Loads ^(1, 2, 3) (psf)			Maximum Span ⁽⁵⁾ (in.)
			Climate Zone			
			1A	1B	2	
15/32, 1/2	32/16 ⁽⁶⁾	24	18	36	59	16
19/32, 5/8	40/20 ⁽⁶⁾	24	30	62	100	20
		32	17	35	56	
23/32, 3/4	48/24 ⁽⁷⁾	32	25	51	81	24
		48	11	23	36	
7/8	60/32 ⁽⁷⁾	48	18	38	61	-
1-1/8	60/48 ⁽⁷⁾	48	18	38	61	-

(1) Load and span ratings developed in accordance with ASTM D5516 and calculated in accordance with ASTM D6305.

(2) The total allowable load is the sum of the live and dead loads at maximum span.

(3) Uniform load deflection limitations 1/180 of span under live load plus dead load, 1/240 under live load only.

(4) For roof slopes less than 3:12, the next panel thickness greater than required for the span shall be specified.

(5) Limited to 100 psf maximum live load.

(6) Plywood conforming to US DOC PS 1 or PS 2 minimum of 4 plies.

(7) Plywood conforming to US DOC PS 1 or PS 2 minimum of 5 plies.



TABLE 3 – FlameTech Treated Lumber Adjustment Factors When Used at or Near Room Temperatures

Property	Lumber Treatment Adjustment Factors ^(1, 2)			
	SPF	Southern Pine	Douglas Fir	Other Wood Species
Bending MOR	0.95	0.82	1.00	0.82
Bending MOE	1.00	0.87	0.99	0.87
Tension Parallel to Grain	0.95	0.98	1.00	0.98
Shear Parallel to Grain	1.00	0.95	1.00	0.95
Compression Parallel to Grain	0.96	0.96	0.96	0.96
Compression Perpendicular to Grain ⁽³⁾	0.95	0.95	0.95	0.95
Fasteners / connectors ⁽⁴⁾	0.90	0.90	0.90	0.90

- (1) Results of matched treated and untreated tests after conditioning at nominal room temperatures (72°F) for service temperatures up to 100°F
- (2) Treatment adjustment factors for test data developed in accordance with ASTM D5664 and calculated in accordance with ASTM D6841.
- (3) Compression Perpendicular assigned according to ASTM D6841 section 9.5
- (4) Fastener/connection assigned according to ASTM D6841 section 9.6

TABLE 4 – FlameTech Treated Lumber Adjustment Factors for Service Temperatures to 150°F

Property	Lumber Treatment Adjustment Factors ⁽¹⁾											
	SPF			Southern Pine			Douglas Fir			Other Wood Species		
	Climate Zone											
	1A	1B	2	1A	1B	2	1A	1B	2	1A	1B	2
Bending MOR	0.94	0.95	0.96	0.81	0.81	0.81	1.00	1.00	1.00	0.81	0.81	0.81
Bending MOE	0.98	0.98	0.98	0.88	0.88	0.88	1.00	1.00	1.00	0.88	0.88	0.88
Tension Parallel to Grain	0.91	0.91	0.91	0.93	0.96	0.99	1.00	1.00	1.00	0.93	0.96	0.99
Shear Parallel to Grain	0.98	0.99	1.00	0.88	0.91	0.94	1.00	1.00	1.00	0.88	0.91	0.94
Compression Parallel to Grain	0.94	0.95	0.96	0.89	0.92	0.95	0.96	0.96	0.96	0.89	0.92	0.95
Compression Perpendicular to Grain ⁽²⁾	0.95	0.95	0.95	0.95	0.95	0.95	0.95	0.95	0.95	0.95	0.95	0.95
Fasteners / connectors ⁽³⁾	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90

- (1) Treatment adjustment factors for test data developed in accordance with ASTM D5664 and calculated in accordance with ASTM D6841
- (2) Compression Perpendicular assigned according to ASTM D6841 section 9.5
- (3) Fastener/connection assigned according to ASTM D6841 section 9.6